



Royce

Royce Associates a Limited Partnership
35 Carlton Avenue
East Rutherford, NJ 07073
Phone: (201)-438-5200
Fax: (201)-438-5207

TECHNICAL DATA SHEET

ROYCE CRYSTAL VIOLET LIQUID

| | |
|-------------------------|----------------|
| Color Index No: | Basic Violet 3 |
| Ionic Character | Cationic |
| Specific Gravity | 1.11 |
| Pounds per Gallon | 9.25 |
| pH as Supplied | 2.0 – 2.8 |
| Viscosity | 200 - 400 cps |
| Artificial Light Change | Redder, Duller |
| Graniting | Slight |
| Optimum pH Range | 4.5 – 7.0 |
| Relative Two-Sidedness | Topsided |
| Affinity for Fibers: | |
| Bleached | Poor |
| Unbleached | Good |
| Lightfastness | Poor |
| Affinity for Fillers: | |
| Clay | Fair |
| Titanium Dioxide | Poor |
| Bleachability | Fair |
| Fastness Properties: | |
| Bleeding in Water | Excellent |